

General Product Description

Protecta® FR Adhesive contains a water based inorganic polymer and filler, and is designed to withstand temperatures greater than 1,200 °C. It is supplied as a ready to use thixotropic paste which exhibits excellent early grab and rapid bond strength.

After curing the product forms a cement with a permanent bond giving excellent adhesion in service.

Protecta® FR Adhesive can be used both as an adhesive and as a filler, with multiple usages where bonding or sealing very hot surfaces is required, or sustaining a seal or a bond within a fire situation without detachment.

Properties

- Ideal for bonding mineral fibre boards to steel, timber and concrete, adding an extra layer of protection against heat transfer
- Ideal for sealing joints on stoves, flues, grates and central heating boilers
- Ideal for sealing annular gaps on high surface temperature pipes
- Ideal for sealing and repairing small cracks and holes in car exhausts systems - stops noise and gas emission leaks
- Suitable for most surfaces, including stone, brick, concrete, cement, plaster, timber, metals, stone wool, glass, paper, vitreous and ceramic surfaces and all inorganic materials (on plastics and painted surfaces, adhesion should be tested)
- Instant grab with no need for additional support (under correct applications)
- High bond strength when cured
- Designed to withstand temperatures above 1,200 °C
- Seals and repairs systems in situ
- Prevents escape of dangerous exhaust fumes from joints and repairs
- Ready to use and easy to apply
- Fast setting - air cures to a hard finish especially when heated, tack free in approx. 1 hour, good bond in 4 hours and full cure in 48 hours
- Slump resistant
- Shock and vibration resistant during service
- No priming necessary for application to most materials
- The fire performance specification of a bond has been derived when the adhesive has been let to cure for only 24 hours
- Product is practically odourless and VOC free
- Alkaline - does not attack acid sensitive substrates
- 18 months storage time (under correct conditions)
- 30 years working life (under correct conditions)

Limitations

- Not intended for application on substrates that can exude certain oils and plasticizers or solvents
- Not suitable for food contact or medical applications
- Cannot be subject to sub-zero temperatures before setting (48 hours)
- Cannot be subjected directly to water or moisture



Resistance to Fire (as an adhesive)

| Substrate | Insulation product | Classification |
|---|---|----------------|
| Steel I beams and columns, and rectangular or circular hollow columns | Mineral fibre stone wool boards or sections ≤ 6.4 kg/m ² (e.g. 40mm thick at 160 kg/m ³) | R 120 *) |

*) Limited by the approval of the mineral fibre boards used. Tested with 20 - 40mm thick Protecta® R-Board (mineral fibre stone wool at 160 kg/m³).

Test Standards & Observations

This Technical Data Sheet's references to fire resistance are based on the product's tests and classifications in accordance with EN 13381-4 and analysis at various design temperatures ranging from 350 °C to 750 °C, in conjunction with the fire resistance test standard EN 1363-1.

The adhesive was subjected to 1,150 °C after 4 hours in the fire tests without any bonded mineral fibre boards detaching, including bonded boards to loaded beams with up to 39mm central vertical deflection.

Tests with the FR Adhesive outperformed comparison tests with CHP welding pins on identical steel sections, suggesting the adhesive adds to the fire resistance compared to normal fixing methods.

The product is CE marked.



General Application Instructions

1. All surfaces must be clean and sound, free from dirt, grease and other contamination that can prevent full bond strength being achieved. Remove any rust by abrading the surface with a wire brush. Loose particles should be cleaned away before applying the Protecta® FR Adhesive.
2. Apply Protecta® FR Adhesive to the prepared surfaces evenly ensuring good contact, clamp immediately and smooth as required. A damp cloth or sponge may be used to remove excess. A little water may be used to smooth the surface if necessary.
3. As the Protecta® FR Adhesive hardens it will form a gas tight seal. Heat will accelerate the cure time.
4. Tools and any excess uncured material may be cleaned with water. Close container after use to preserve unused product.

Additional Instructions Bonding Mineral Fibres

1. Mineral fibre boards have a degree of loose fibres on the board surfaces, and to secure a good bond, it is recommended to apply a thin coating of Protecta® FR Adhesive to the boards on the areas that will be bonded to the substrate. Adhesive can be thinned slightly with clean water to reduce viscosity if required. All excess adhesive must be removed.
2. Leave to skin and dry (this will be in a relatively short space of time depending on atmospheric conditions).
3. Apply adhesive to the substrate with 5 x 5mm toothed trowel leaving a uniform continuous toothed bed of Protecta® FR Adhesive. Do not allow to skin.
4. Place the board on the bed of adhesive. Once in place give the board a side to side movement to aid suction and contact to the adhesive.
5. Fill any gaps between boards using Protecta® FR Adhesive contained in a sealant cartridge using a nozzle with the appropriate sized opening.
6. All tools should be kept clean during and after each application; it is advised to keep tools in a bucket of clean water to prevent the adhesive setting on the tools.

These instructions should be used in conjunction with the approvals and instructions for the mineral fibre boards selected for the project.

Emission Data (indoor air quality)

| Compound | Emission rate after 3 days | Emission rate after 4 weeks |
|--------------|----------------------------|-----------------------------|
| TVOC | < 5 µg/m ³ | < 5 µg/m ³ |
| TSVOC | < 5 µg/m ³ | < 5 µg/m ³ |
| VOC w/o NIK | < 5 µg/m ³ | < 5 µg/m ³ |
| R Value | 0 | 0 |
| Formaldehyde | < 3 µg/m ³ | < 3 µg/m ³ |
| Acetaldehyde | < 3 µg/m ³ | < 3 µg/m ³ |
| Sum for+ace | < 0.005 ppm | < 0.005 ppm |
| Carcinogenic | < 1 µg/m ³ | < 1 µg/m ³ |

| Regulation or Protocol | Conclusion |
|--------------------------------------|-----------------|
| French VOC Regulation | A+ |
| French CMR components | Pass |
| Italian CAM | Pass |
| ABG / AgBB to the guidelines of DIBt | Pass |
| Belgian Regulation | Pass |
| EMICODE | EC 1 PLUS |
| Indoor Air Comfort GOLD® | Pass |
| Blue Angel (DE-UZ 123) | Pass |
| BREEAM-International | Exemplary Level |
| BREEAM-NOR | Pass |
| M1 Protocol | Pass |
| LEED v4 & v4.1 | Compliant |

Protecta® FR Adhesive has been tested by Eurofins Product Testing; reports available upon request.

Technical data

| | |
|-----------------------|--|
| Condition | Ready for use paste |
| Cure system | Water loss, hardens in air and especially at raised temps. |
| Specific gravity | 1.7 - 1.9 |
| Flash point | None |
| Colour | Beige |
| Odour | Barely perceptible odour |
| Evaporation rate | Negligible |
| Solubility in water | Soluble |
| Viscosity | Viscous |
| pH | 11.0 |
| Solids content (%w/w) | > 70 % |
| Flexibility | None |
| Tack free | Approx. 60 minutes |
| Film forming | Approx. 10 minutes |
| Totally hardened | 12 to 48 hours depending on temperature |
| Application temp. | + 5 °C to + 30 °C (during application and curing) |
| Service temperature | - 50 °C to + 1,200 °C (avoid condensation on product) |
| Shelf life & storage | Up to 18 months if stored in unopened containers under cool dry conditions between 10 °C and 30 °C |
| Working life | Minimum 30 years if protected from water/moisture contact |
| Packaging | Box containing 25 cartridges each 310 ml Pails containing 10 ltr Pallets 310 ml: 64 boxes per pallet equals 1600 pcs |

Health and Safety

Keep container tightly closed when not in use. Use the product in a well-ventilated area. Avoid contact with the eyes and skin. Wash the material from the skin while still wet using water. Material in contact with eyes should be washed out immediately with water. Seek medical advice if discomfort persists. More detailed information can be found in the relevant Protecta® Safety Data Sheet.